

Film protettivo 219.02.220A

			_
Properties	Test procedures	Unit of measure	Values and Characteristics
Environmental condit. Temperature Atmospheric pressure Relative humidity		Celsius degree mmHg %	20°+/-10% 760 +/- 5% 80 +/-10%
Backing material			Transparent Polyolefins
Type of adhesive			Acrylic
Total thickness	AFERA 4006	mm.	0,028 +/- 10%
Backing tensile strength	ASTM D882	MD N/mm2. TD	>32 >22
Backing elongation at break	ASTM D882	MD % TD	>250 >750
Adhesion to steel	AFERA 4001 (*)	cN/25 mm.	235 +/- 20%
Shelf life Storage	Internal method	month	6 at room temp.
Resistance Against	Moisture	Oil / Plasticizers	

Resistance Against	Moisture	Oil / Plasticizers	
	Moderate	Low	

## (\*) Modified according to internal method for protective tapes

Please note: environmental conditions do affect the adhesion level; some variations can be found even at slightly different temperatures (+/- 1  $^{\circ}$  C. ) from the stated ones. These variations do not change the general features of the product.

All statements contained in this sheet are based on tests we believe reliable but the accuracy or completeness is not guaranteed.

Before using, user shall determine the suitability of the product for his intended use and user assumes all risks and liability, whatsoever, in connection therewith.

The company reserves the right to improve products and change specifications which may alter performance.