

## FILM PROTETTIVO C 400

Properties	Test procedures	Unit of measure	Values and Characteristics
Environmental			
condit.		Celsius degree	20°+/-10%
Temperature		mmHg	760 +/- 5%
Atmospheric		%	80 +/-10%
pressure			
Relative humidity			
Backing material			Transparent Polyolefins
Type of adhesive		-	Rubber
Type of aunesive		+	Kuuuci
Total thickness	AFERA 4006	mm.	0,047 +/- 10%
		MD	> 23
Backing tensile	ASTM D882	N/mm2.	
strength		TD	> 17
		MD	> 300
Backing elongation	ASTM D882	%	<50
at break		TD	> 650
Adhesion to steel	A EED A 4001 (*)	cN/25 mm.	35 +/- 15
Addresion to steet	AFERA 4001 (*)	CIN/23 IIIIII.	33 +/- 13
		†	
Shelf life Storage	Internal method	month	6 at room temp.
Resistance Against	Moisture	Oil / Plasticizers	

## (\*) Modified according to internal method for protective tapes

High

Please note: environmental conditions do affect the adhesion level; some variations can be found even at slightly different temperatures (+/- 1  $^{\circ}$  C) from the stated ones. These variations do not change the general features of the product.

None

All statements contained in this sheet are based on tests we believe reliable but the accuracy or completeness is not guaranteed.

Before using, user shall determine the suitability of the product for his intended use and user assumes all risks and liability, whatsoever, in connection therewith.

The company reserves the right to improve products and change specifications which may alter performance.