

685/041/GA/173

Issued on 15/03/2016

Test procedures	Unit of measure	Values and Characteristics
•		
	Celsius degree	20°+/-10%
	mmHg	760 +/- 5%
	%	80 +/-10%
		PP Transparent
		Acrylic
AFERA 4006	mm.	0,049 +/- 10%
DINI EN 190 527 1	MD	>57
DIN EN ISO 527-1	N/mm2. TD	>34
DN1 DN1 00 505 1	MD	>570
DIN EN ISO 527-1	% TD	>560
AFERA 4001 (*)	cN/25 mm.	800 +/- 20%
Internal method	month	6 at room temp.
	AFERA 4006 DIN EN ISO 527-1 DIN EN ISO 527-1	Celsius degree mmHg % AFERA 4006 mm. DIN EN ISO 527-1 MD N/mm2. TD MD DIN EN ISO 527-1 % TD AFERA 4001 (*) cN/25 mm.

Resistance Against	Moisture	Oil / Plasticizers	Anchorage
	High	Moderate	500

(*) Modified according to internal method for protective tapes

Please note: environmental conditions do affect the adhesion level; some variations can be found even at slightly different temperatures (+/- 1 $^\circ$ C.) from the stated ones. These variations do not change the general features of the product.

All statements contained in this sheet are based on tests we believe reliable but the accuracy or completeness is not guaranteed.

Before using, user shall determine the suitability of the product for his intended use and user assumes all risks and liability, whatsoever, in connection therewith.

The company reserves the right to improve products and change specifications which may alter performance.